

# Cleanz™



No mold. No mildew. No scrubbing needed!

**DESCRIPTION:**

**Why does mold grow so quickly?  
Because you're feeding it!**

Mold feeds on body oils, shower products, cooking oils, and bacon grease that collect in the corners of your shower and kitchen. That's why we created Cleanz™, the first ever active enzyme caulk that breaks down these oils - eliminating mold food.

By taking away the food, we literally strip mold of its power to grow. Plus, unlike mildewcides and repellants that wear out over time, our enzymes are permanently active for long-lasting results!

**WHERE TO USE:**

- Countertops
- Backsplashes
- Kitchen fixtures
- Bathroom fixtures
- Bathtubs
- Showers
- Sinks

**PAINTABILITY:**

Paint will interfere with enzymes in Cleanz™.

**FEATURES**

- No mold
- Ultra-elastic
- Great adhesion
- Won't wear or tear
- Easy to use
- Low VOC
- Zero Risk

**ADHERES TO:**

Most building materials including:

**Metals**

- Aluminum
- Steel
- Nickel

**Plastics**

- ABS
- Vinyl
- Acrylic Sheet
- PVC
- Plexiglass
- Fiberglass (uncoated)

**Other Surfaces**

- Glass
- Granite
- Porcelain
- Formica®\*\*
- Drywall
- Ceramic tile
- Marble
- Cement
- Wood
- Slate
- Corian®\*\*

**COVERAGE:**

A 10.5 oz. cartridge will yield approx. 26 lineal feet with a ¼" (6 mm) bead. A 6 oz. tube will cover approx. 16 lineal feet with a ¼" (6 mm) bead which is equal to one average tub enclosure.

**BENEFITS**

- Active enzymes stop mold before it has a chance to grow.
- Moves with your house. Won't crack.
- Won't pull away from bathtub (or any other surface). Maintains watertight seal.
- Resilient surface withstands scrubbing and chemical cleaners.
- Smooth application, quick water cleanup and no offensive smells.
- Meets strictest VOC requirements. Environmentally friendly.
- Satisfaction guaranteed, or we'll pay a contractor to fix it!\*



White 10.5 oz & 6 oz  
Almond 6 oz

\*Learn more at [TryCleanz.com/Warranty](http://TryCleanz.com/Warranty)

\*\* Corian® and Formica® are registered trademarks of their respective owners.

#### WHERE NOT TO USE:

- Areas submerged in water (such as pools, drains, hot tubs or saunas).
- Cleanz™ will discolor copper and brass. Use Sashco's Lexel® instead.
- Will not adhere to or is incompatible with polypropylene, waxes, polyethylene, and silicone.

#### INSTRUCTIONS:

1. Remove previously applied caulk, dirt, soap scum, and mold. If silicone caulk is present, use a liquid caulk remover to ensure new caulk will stick.
2. Sanitize the joint using a 1:9 bleach to water mixture scrubbing well with a brush. Rinse with water and dry.
3. Cut nozzle at a 45° angle to a minimum of 1/4" opening.
4. Rest the nozzle on the joint and pull along as you extrude material.
5. To smooth out bumps gently press Cleanz onto the sides of the joint using your finger or foam brush and soapy water or clear window cleaner. Clean hands and surfaces with soap and water. Allow 24 to 48 hours dry time (depends on humidity) before exposure to water.

#### STORAGE:

Tightly reseal with cap and/or plastic wrap and rubber band. Store between 40°F and 90°F.

VOC Content: 67 g/L, <1.5% wt.

#### Satisfaction guaranteed, or we'll pay a contractor to fix it!

Sashco's promise is 'Products That Work'. We will actually pay someone to re-caulk for you if mold grows on properly installed Cleanz or it otherwise fails in the first 7 years after purchase. Proof of purchase is required. Warranty applies to single family residential use only; no other warranties are implied. Sashco will not be responsible for consequential damages other than product reinstallation. Learn more at [TryCleanz.com/Warranty](http://TryCleanz.com/Warranty).

#### TYPICAL PROPERTIES:

Property	Value
Joint Size	Maximum 2"
Application Range	40°F to 100° F (4°C to 38°C) surface temperature
Service Range	0°F to 115° F (-17°C to 46°C)
Tensile Properties	Maximum Stress: 150 psi Elongation to Break: 500%
VOC	67 g/L, <1.5% by wt.

#### TEST DATA:

Property	Results	Test Method
Hardness, Shore A	55 (21 day cure)	ASTM C661
Slump	< 1/8"	ASTM D2202
Solids	77% by weight	ASTM C1250
Freeze-Thaw Stability	Passes 10 cycles (-15°F to 70°F) (-26°C to 21°C)	ASTM C731
Low Temp. Flexibility	Pass (not artificially weathered)	ASTM C734
Tack-free	30 minutes	ASTM C679
Water resistant	24 to 48 hours (depends on humidity)	Internal Test
Cured	4-5 days (dependent on temperature, humidity and bead size)	ASTM C679
Adhesion-in-peel Passing Substrates	See "ADHERES TO" section on front page	ASTM C794

#### SPECIFICATIONS:

- Meets FHA requirements.
- Meets or exceeds Federal Specification: ASTM C834

The data reported here are believed to be reliable.  
No warranty is made concerning the accuracy of or the results obtained from their use.

**CAUTION:** Avoid contact with eyes and skin. Do not swallow. In case of eye or skin contact, flush thoroughly with water. If irritation persists contact a physician. If swallowed administer two glasses of water and contact a physician immediately. KEEP OUT OF REACH OF CHILDREN.

**⚠ WARNING:** Cancer and Reproductive Harm - [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov).